

Technical datasheet

Coarse filter mat K15/350 (regenerable)

Basic information	Specification
Basic elastomer	PES
Fabric ply	without ply
Description/features	Fibres solidified without additional binding agents, high mechanical resistance and high dust efficiency and dust storage capacity, multiple-use possible due to easy cleaning, temperature resistant
Areas of application	fans, ventilation systems, climatic testing chest, climatic test cabinet
Format	Rolls: 16 mm available in: 20 m x 2 m
Colour	white


Technical data	Standard term/Specification	Unit	Testing method
Density	0.30	g/cm ³	DIN EN ISO 1183-1
Filter class	G 3		DIN EN 779
Medium dust efficiency	about 89	%	DIN EN 779
Dust storage capacity	about 520	g/m ²	DIN EN 779
Thickness	about 16	mm	
Fire performance	F1 self-extinguishing		DIN 53438
Initial differential pressure	45	Pa	544 m ² /hxm ² (1.5 m/s.) DIN EN 779
Final pressure drop, recommended	250	Pa	DIN EN 779
Temperature range	+ 100	°C	

Resistance	Standard term/Specification
Oil	n.sp.
Fuels	n.sp.
Acids	n.sp.
Alkaline solution	n.sp.
Weather	n.sp.

Legend
⊕ ⊕ = particularly resistant ⊖ = not resistant n.sp. = not specified ⊕ = resistant n.a. = not applicable

Product-related special properties can be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1019.



elastomer
technology