

# Technical datasheet

## NBR 70 - round cord quality

Basic information	Specification
Basic elastomer	NBR
Fabric ply	without ply
Description/features	NBR-quality
Format	<b>bouquets:</b> 2 mm up to 3 mm available in 200 m 4 mm up to 7 mm available in 100 m 8, 10, 12, 14 mm available in 50 m 15, 16, 18, 19, 20, 21, 22, 25 mm available in 25 m 30 mm available in 20 m 40 mm available in 10 m
Colour	black


Technical data	Standard term/Specification	Unit	Testing method
Density	1.30	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Shore A	70 ± 5	°ShA	DIN ISO 7619-1
Tensile strength	7.5	N/mm <sup>2</sup>	DIN 53504
Elongation at break	150	%	DIN 53504
Abrasion	n.sp	mm <sup>3</sup>	DIN ISO 4649 method A
Ozone	from - 25 up to + 110	°C	

Resistance	Standard term/Specification
Oil	⊕ ⊕
Fuels	⊕
Acids	⊖
Alkaline solution	⊖
Weather	⊖
Solvent	⊖

Legend
⊕ ⊕ = particularly resistant      ⊖ = not resistant      n.sp. = not specified ⊕ = resistant      n.a. = not applicable

Product-related special properties may be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.  
 \*order-relate only

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 0520.



elastomer  
technology