

Technical datasheet

NK sponge rubber grade

Basic information	Specification
Basic elastomer	NR
Fabric ply	without ply
Description/features	film on both sides, coars fabric pattern on both sides, good temperature resistance
Format	Rolls: 2 mm to 10 mm thickness available in 1 m x 10 m Sheets: 2 mm to 10 mm thickness available in 1 m x 1 m or 1 m x 2 m 12 mm to 50 mm thickness available in 1 m x 1 m
Colour	black*

Technical data	Standard term/Specification	Unit	Testing method
Density	0.5 to 0.9	g/cm ³	DIN EN ISO 1183-1
Shore A	18	°ShA	DIN ISO 7619-1
Tensile strength	about 1.0	N/mm ²	DIN 53504
Elongation at break	200 to 400	%	DIN 53504
Abrasion	n.a.	mm ³	DIN ISO 4649 method A
Compression set**	about 35	%	DIN ISO 815-1
Temperature range	from - 40 up to + 70	°C	

Resistance	Standard term/Specification
Oil	⊖
Fuels	⊖
Acids	n.sp.
Alkaline solution	n.sp.
Weather	⊕

Legend
⊕ ⊕ = particularly resistant ⊖ = not resistant n.sp. = not specified ⊕ = resistant n.a. = not applicable

Product-related special properties can be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.

* Production related colour deviations to the point of dark grey possible.

** 50% deformation in 24 h at 23 °C

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 0823.



elastomer
technology