

Technical datasheet

PU 75 dark blue

Basic information	Specification
Basic elastomer	Polyurethane
Fabric ply	without ply
Description/features	Premium PU-quality with excellent mechanical properties especially with high wear resistance and elasticity and low abrasion
Format	Sheets: 2 m x 1 m
Colour	dark blue


Technical data	Standard term/Specification	Unit	Testing method
Density	1.24	g/cm ³	DIN EN 53 479
Shore A	75	°ShA	DIN 53 305
Tensile strength	45	N/mm ²	DIN 53 504
Elongation at break	550	%	DIN 53 504
Abrasion	20	mm ³	DIN ISO 4649 method A
Tear strength	40	kN/m	DIN 53 515
Compression set 20 °C, 72 h	20	%	DIN 53 517
Compression set 70 °C, 24 h	30	%	DIN 53 517
Impact resilience	50	%	DIN 53 512
Temperature range	from - 40 to + 80	°C	

Resistance	Standard term/Specification
Oil	n.sp.
Fuels	n.sp.
Acids	n.sp.
Alkaline solution	n.sp.
Weather	n.sp.
UV	n.sp.

Legend
⊕ ⊕ = particularly resistant ⊖ = not resistant n.sp. = not specified ⊕ = resistant n.a. = not applicable

Product-related special properties can be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.
 *Extreme colour deviations possible depending on manufacturer.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1119.



elastomer
technology