

Technical datasheet

PVC "anti-static"

Basic information	Specification
Basic elastomer	PVC
Fabric ply	without ply
Description/features	PVC is transparent, hard and brittle. By adding plasticizers and stabilizers PVC becomes softer, mouldable and suitable for technical applications. PVC plays a key role in the construction industry and has good mechanical and electrical properties. Being antistatic, it is virtually impossible to electrically charged PVC.
Format	Rolls: 20 m x 1 m
Colour	transparent

Technical data	Standard term/Specification	Unit	Testing method
Density	1.22	g/cm³	DIN EN ISO 1183-1
Shore A	78	°Sh A	DIN 53 505
Tensile strength	20	N/mm²	DIN EN ISO 527-3
Elongation at break	355	%	DIN EN ISO 527-3
Abrasion	n.sp.	n.sp.	
Compression set	> 55	N/mm	DIN 53 515
Temperature range	-30 up to +60	°C	DIN 53 372

Electrical properties	Standard term/Specification	Unit	Testing method
Outer surface coefficient after production after 6 months storage time	ca. 2.1 x 10 ⁸ ca. 6.0 x 10 ⁷	Ω	IEC 93
Specific volume resistance	ca. 1.0 x 10 ⁸	Ω	IEC 93

Resistance	Standard term/Specification	
Oil	n.sp.	
Fuels	n.sp.	
Acids	n.sp.	
Alkaline solution	n.sp.	
Weather	n.sp.	

Legend		
+ + = particularly resistant + = resistant	= not resistant	n.sp. = not specified n.a. = not applicable

Prodct-related special properties can be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 0721.

