

# Technical datasheet

## isoplan® 750

Basic information	Specification
Basic elastomer	n.a.
Fabric ply	mineral fibres
Description/features	Insulation material on the basis of mineral fibres featuring high application limit temperatures and low thermal conductivity
Format	<b>Rolls:</b> 1.5 mm to 10 mm available in 1 m x 1 m
Binding agent	organic
Colour	white with green honeycomb print


Technical data	Standard term/Specification	Unit	Testing method
Density	0.94	g/cm <sup>3</sup>	DIN 28 090-2
Tensile strength	3.5	N/mm <sup>2</sup>	DIN 52 910
Compression	<25	%	ASTM F 36 K
Resilience	>25	%	ASTM F 36 K
Loss on ignition	17	%	DIN 52 911
Shrinkage of thickness	2.5	%	1 h/800 °C
Surface shrinkage	< 2.0	%	1 h/800 °C
Thermal conductivity	0.13	W/(m*K)	400 °C medium temperature
Temperature range	+750	°C	

Resistance	Standard term/Specification
Oil	n.sp.
Fuels	n.sp.
Acids	n.sp.
Alkaline solution	n.sp.
Weather	n.sp.

Legend
(+) (+) = particularly resistant      (−) = not resistant      n.sp. = not specified (+) = resistant      n.a. = not applicable

Product-related special properties can be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1019.



elastomer  
technology