

Technical datasheet

PC (Polycarbonat) Food Grade

Example of application
<ul style="list-style-type: none"> › machine covers, safety covers › food packaging › suitable for contact with food products

Advantage	Disadvantages
<ul style="list-style-type: none"> › useable from -40 °C to +115 °C › self-extinguishing › could mouldable › FDA- and EU-compliant 	<ul style="list-style-type: none"> › poor chemical resistance › moisture ingress › susceptibility to scratching

Basic information	Specification
Format	Sheets: 2, 3, 4, 5, 6, 8, 10, 12 and 15 mm available in 3.05 m x 2.05 m

Physical properties	Standard term/Specification*	Unit	Testing method
Density	1.2	g/cm ³	DIN EN ISO 1183
Moisture ingress	n.sp.	%	DIN EN ISO 62

Mechanical properties	Standard term/Specification*	Unit	Testing method
Tensile strength	60	N/mm ²	DIN EN ISO 527
Elongation at break	80	%	DIN EN ISO 527
E-module	2.200	N/mm ²	DIN EN ISO 527
Notch toughness	fracture free	kJ/m ²	DIN EN ISO 179
Rockwellhardness	n.sp.	n.sp.	DIN EN ISO 2039-1

Thermal properties	Standard term/Specification*	Unit	Testing method
Thermal conductivity	0.2	W/(m·K)	DIN 52612
Linear thermal expansion coefficient	0.65	K ⁻¹ ·10 ⁻⁴	DIN 53752
	1.3	mm	At initial length of 1.000 mm and a temperature difference of 20 °C
Max. operating temperature, short-term	130	°C	
Min. operating temperature, long-term	-40	°C	
Max. operating temperature, long-term	115	°C	

Electrical properties	Standard term/Specification*	Unit	Testing method
Resistance	10 ¹⁵	Ω·cm	DIN 53482
Outer surface coefficient	> 10 ¹⁵	Ω	DIN 53482
Puncture resistance	> 30	kV/mm	DIN 53481

Legend
n.sp. = not specified

*higher specification on request.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1219.



transparent
plastics