

Technical datasheet

PC anti-static coating (polycarbonate)

Example of application
<ul style="list-style-type: none"> › With special coating to prevent electrostatic charging (e.g. for covers and housings) › Insulating parts for the electrical industry › Partitions, acoustic barriers

Advantage	Disadvantages
<ul style="list-style-type: none"> › ESD-conductive › Good transparency (about 85 %) › Physiologically inert › Self-extinguishing and cold mouldable 	<ul style="list-style-type: none"> › Susceptibility to scratching › Moisture ingress › Poor chemical resistance

Basic information	Specification
Format	Sheets: 3 - 6, 8 and 10 mm available in 2 m x 3 m

Physical properties	Standard term/Specification*	Unit	Testing method
Density	1.2	g/cm ³	DIN EN ISO 1183
Moisture ingress	0.35	%	DIN EN ISO 63

Mechanical properties	Standard term/Specification*	Unit	Testing method
Tensile strength	60	N/mm ²	DIN EN ISO 527
Elongation at break	> 80	%	DIN EN ISO 527
E-module	2.200	N/mm ²	DIN EN ISO 527
Notch toughness	fracture free	kJ/m ²	DIN 53453
Rockwellhardness	n.sp.	n.sp.	
Thickness	< 1	µm	

Thermal properties	Standard term/Specification*	Unit	Testing method
Thermal conductivity	0.2	W/(m·K)	DIN 52612
Linear thermal expansion coefficient	0.65	K ⁻¹ ·10 ⁻⁴	DIN 53752
	1.3	mm	At initial length of 1.000 mm and a temperature difference of 20 °C.
Max. operating temperature, short-term	135	°C	
Max. operating temperature, long-term	115	°C	

Electrical properties	Standard term/Specification*	Unit	Testing method
Resistance	10 ¹⁶	Ω·cm	DIN IEC 60093
Outer surface coefficient	10 ⁴ -10 ⁹	Ω	ASTM D257
Puncture resistance	35	kV/mm	IEC 60243

Legend
n.sp.= not specified

*Higher specification on request.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 12/19.



transparent
plastics