

Technical datasheet

PEEK MG (Polyetheretherketone medical grade)

Example of application
› medical technology

Advantages	Disadvantages
› excellent chemical resistance › very high temperature resistance › very good mechanical properties	› expensive

Basic information	Specification
Format	round material: 6 mm up to 100 mm available in 3 m length sheets: 6 mm up to 60 mm available in 3 m x 0.62 m

Physical properties	Standard term/Specification*	Unit	Testing method
Density	1.31**	g/cm ³	ISO 1183
Moisture ingress	0.2	%	DIN EN ISO 62

Mechanical properties	Standard term/Specification*	Unit	Testing method
Tensile strength	110	MPa	DIN EN ISO 527
Elongation at break	20	%	DIN EN ISO 527
E-Module	4,000	MPa	DIN EN ISO 527
Notch toughness	n.sp.	kJ/m ²	ISO 179
Rochwellhardness	230	MPa	DIN EN ISO 2039

Thermal properties	Standard term/Specification*	Unit	Testing method
Thermal conductivity	0.25	W/(m·K)	DIN 52612
Linear thermal expansion coefficient based on a fixed initial length	0.5	K ⁻¹ · 10 ⁻⁴	DIN 53752
	1.0	mm	At initial length of 1.000 mm and a temperature difference of 20 °C.
Max. operating temperature, long-term	250	°C	
Max. operating temperature, short-term	310	°C	
Min. operating temperature, long-term	-60	°C	

Electrical properties	Standard term/Specification*	Unit	Testing method
Resistance	4.9 · 10 ¹⁶	Ω·cm	DIN IEC 60093
Outer surface coefficient	10 ¹⁸	Ω	DIN IEC 60093
Puncture resistance	20	kV/mm	DIN EN 60243

Legend
n.sp. = not specified

Should you require binding and exact values, please ask for the appropriate factory certificate. This may incur additional costs. Please note that all specifications are standard values only, which are subject to production-related fluctuations.

*Higher specification on request. ** Density based on PEEK MG natural, may deviate with coloured variations.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 01.23.



technical
plastics