

Technical datasheet

PMMA GS (cast polyamide)

Example of application
<ul style="list-style-type: none"> › Roofing, windbreak, covers, vacuum lid › Signage und displays › Housing, furniture › Decoration

Advantage	Disadvantages
<ul style="list-style-type: none"> › Visually appealing › Brilliant transparency › Mechanical resistance and good weatherproof › Scratch resistance 	<ul style="list-style-type: none"> › Susceptibility to breakage › Susceptible to cleaning agents containing alcohol

Basic information	Specification
Format	Sheets: 3 – 6, 8, 10 ,12, 15, 20, 25, 30, 40, 45, 50 mm available in 2.03 m x 3.05 m

Physical properties	Standard term/Specification*	Unit	Testing method
Density	1.19	g/cm ³	DIN EN ISO 1183
Moisture ingress	0.2	%	DIN EN ISO 62

Mechanical properties	Standard term/Specification*	Unit	Testing method
Tensile strength	75	N/mm ²	DIN EN ISO 527
Elongation at break	4	%	DIN EN ISO 527
E-module	3.210	N/mm ²	DIN EN ISO 178
Notch toughness	12	kJ/m ²	DIN EN ISO 179
Rockwellhardness	102	M-scale	DIN EN ISO 2039

Thermal properties	Standard term/Specification*	Unit	Testing method
Thermal conductivity	0.19	W/(m·K)	DIN 52612
Linear thermal expansion coefficient	0.7	K ⁻¹ ·10 ⁻⁴	DIN 53752
	1.4	mm	At initial length of 1.000 mm and a temperature difference of 20 °C.
Max. operating temperature, short-term	90	°C	
Max. operating temperature, long-term	80	°C	

Electrical properties	Standard term/Specification*	Unit	Testing method
Resistance	10 ¹⁵	Ω·cm	DIN 53482
Outer surface coefficient	10 ¹⁴	Ω	DIN 53482
Puncture resistance	n.sp.	kV/mm	DIN 53481

Legend
n.sp.= not specified

*Higher specification on request.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1020.



transparent
plastics